

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : C09B 69/00, C09D 11/10, C09B 67/22, C09D 11/02</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/31189 (43) International Publication Date: 2 June 2000 (02.06.00)</p>
<p>(21) International Application Number: PCT/US99/27038 (22) International Filing Date: 15 November 1999 (15.11.99) (30) Priority Data: 09/198,113 23 November 1998 (23.11.98) US (71) Applicant: SUN CHEMICAL CORPORATION [US/US]; 222 Bridge Plaza South, Fort Lee, NJ 07024 (US). (72) Inventors: LAKSIN, Mikhail; 2278 Redwood Road, Scotch Plains, NJ 07076 (US). CHATTERJEE, Subhankar; 60 Norma Road, Hampton, NJ 08827 (US). SCHWARTZ, Russell; 8300 Monte Drive, Cincinnati, OH 45232 (US). MERCHAK, Paul, A.; 10063 Fox Chase Drive, Loveland, OH 45140 (US). AURENTY, Patrice; 27 Charter Oak, Woodridge, NJ 07075 (US). STONE, Edward; 4 Inwood Road, Morris Plains, NJ 07950 (US). KOTORA, Gordon; 29 Belgrade Avenue, Clifton, NJ 07013 (US). (74) Agent: PERSLEY, Sidney; 222 Bridge Plaza South, Fort Lee, NJ 07024 (US).</p>		<p>(81) Designated States: CA, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>
<p>(54) Title: ENERGY CURABLE GRAVURE AND INK JET INKS INCORPORATING GRAFTED PIGMENTS (57) Abstract Solvent-free, energy curable low viscosity gravure and ink jet inks which contain a pigment; a rheological additive having the structure P-(U-Y)_s, wherein P is the residue of an organic pigment or dye, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3; and an energy curable liquid vehicle which may be an ultraviolet cationic, thermal cationic or a free radical initiated polymerization system, cured by actinic radiation; and optionally containing a photoinitiating system.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UC	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

5 ENERGY CURABLE GRAVURE AND INK JET INKS INCORPORATING
GRAFTED PIGMENTS

10 RELATION TO OTHER PATENT APPLICATIONS

This application is a continuation-in-part of U.S.
patent application Ser. No. 08/878,590 filed June 19,
1997.

15 BACKGROUND OF THE INVENTION

Field of the Invention

This invention relates to low viscosity energy
curable gravure and ink jet printing inks and methods for
20 using same.

Description of Related Art

Low viscosity and good flow are the most important
factors affecting liquid ink behavior and improved
25 printability. These factors are particularly important
for formulating inks for ink jet and gravure printing
applications.

Schwartz et al. in U.S. Patent 4,468,255, disclose
rheology modifiers for arylide yellow pigment
30 dispersions. The rheology modifiers which are derived
from diarylide pigments improve the fluidity of non-
aqueous arylide pigment dispersions prepared from either
monoarylide or diarylide yellow pigments. Schwartz et
al. in a series of patents (i.e., U.S. Patents 4,946,508;
35 4,946,509; 5,024,698; and 5,062,894) have disclosed
modified azo pigments for use in conventional, solvent
and water based inks and coatings to function as rheology
control agents. In each of these patents, Schwartz et

5 al. modify an azo pigment (e.g., a diarylide pigment, a
monoazo pigment, a disazo pyrazolone pigment and the
like) by grafting a polyalkylene oxide to the pigment so
that water based inks made from these pigment
compositions exhibit high coloring strength, cleaner
10 shades, lower rheology, and enhanced gloss compared with
conventional water based inks.

To increase printing throughput, ultraviolet (UV) or
electron beam (EB) curable inks have been developed that
allow printers to reduce the solvent content of the ink.
15 It is always a challenging task for a UV or EB curable
liquid ink formulator to develop ink formulations with a
viscosity low enough for improved flow, while at the same
time maintaining other essential characteristics, such as
to cure, adhesion, low odor, etc. Traditional organic
20 and inorganic pigments used in formulating energy curable
liquid inks, are poorly dispersed in the vehicles used in
the systems. As a result, poor pigment wetting leads to
a thixotropic structure. If the inks are not subjected
to high shear, the apparent viscosity will remain high
25 and the ink will exhibit poor transfer resulting in poor
printability. Flow additives have been tried, however,
with limited success for different pigments. The
situation becomes more critical in the case of cationic
curable inks; where not all the pigments and additives
30 can be used due to the presence of basic functionalities.
In addition, some energy curable inks of the prior art
contain fugitive solvent (such as water, alcohols and the
like) as part of the vehicle to reduce viscosity, aid in
pigment dispersion, and modify flow during printing.
35 However, after printing but before curing, the fugitive
solvent is typically removed to prevent interference with
the curing process and to prevent it from having an
adverse affect on the printed image. The curing delay
required by solvent removal, as well as attendant

5 unpleasant odors, are further undesirable limitations to printing. Furthermore, solvent removal is desirable for environmental reasons.

A UV-cured cationically polymerized printing ink is disclosed by Seng in Patent Application DE 195 00 968.1
10 for use in indirect letterpress printing or dry offset printing. Seng lists the differences between letterpress and flexographic printing and the list includes critical differences in ink viscosities. In particular, Seng discloses that printing inks used in flexographic
15 printing have viscosities in the range of 0.01 to 2 cps and at 20°C in the range of 3.0 to 100.0 cps, and more preferably in the range of 4.0 to 10 cps. Seng's inks are cationically polymerized and differ from the very high viscosity printing inks used in indirect letterpress
20 printing in solvent content. While inks of this viscosity range are useful in high shear, indirect letterpress printing, such inks have high tack which causes them to be unsuitable for low shear applications such as flexography, which requires low tack inks.

25 Although improvements have been made in energy curable cationic ink formulations, there continues to be a need for energy curable ink formulations (including free radical initiated curable formulations) which have a high color strength, cleaner shade and enhanced gloss but
30 retain a very low viscosity as required by flexographic and ink jet printing.

SUMMARY OF THE INVENTION

35 In one aspect, the invention is an energy curable gravure ink comprising a pigment, a rheological additive having the structure:

P-(U-Y)_n

5 wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3; and an energy curable liquid vehicle; wherein the ink
10 is substantially free of fugitive solvent and has a viscosity ranging from about 8 cps to about 200 cps.

In another embodiment of this invention, this energy curable gravure ink further comprises a polymerization initiating system activatable by actinic radiation.

15 Another embodiment of this invention involves a method of gravure printing and curing the gravure ink composition comprising the steps of: preparing the energy curable gravure ink described supra; printing the ink onto a substrate surface to form an ink image; and
20 subjecting the ink image to actinic radiation or thermal energy to form a cured ink image.

Another aspect of this invention involves an energy curable ink jet ink comprising a pigment, a rheological additive having the structure:

25



wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety
30 covalently bonding Y to P and s is an integer from 1 to 3; and an energy curable liquid vehicle; wherein the ink is substantially free of fugitive solvent and has a viscosity ranging from about 8 cps to about 200 cps.

In another embodiment of this invention, this energy
35 curable ink jet ink further comprises a polymerization initiating system activatable by actinic radiation.

A further embodiment of this invention involves a method of ink jet printing and curing an ink jet ink composition comprising the steps of: preparing the energy

5 curable ink jet ink described supra; printing the ink onto a substrate surface to form an ink image; and subjecting the ink image to actinic radiation or thermal energy to form a cured ink image.

10

DETAILED DESCRIPTION OF THE INVENTION

The present invention is directed to a novel solvent-free, energy curable gravure and ink jet printing inks having low to very low viscosities and their application. The term "energy curable or cured" as used
15 herein, in reference to ink means an ink which can be cured, hardened, polymerized, or crosslinked by the action of actinic radiation such as UV or EB radiation and the like from a radiant energy source; or from a
20 thermal energy source by heating with a conductive or radiant heat source such as a platen, an oven, infrared (IR), microwave, and the like.

The energy curable ink of this invention comprises a pigment composition and an energy curable liquid vehicle
25 is substantially free of a fugitive solvent. The terms "substantially free of fugitive solvent" and "solvent-free", as used herein in reference to inks, means free of a liquid component (e.g., water, lower alcohols, alkanes, aromatics, aliphatics, ketones, acetates and the like)
30 which, after printing, is evaporated, imbibed into a substrate surface, or both, and does not remain as an essential component of the cured ink. Further, these terms are not intended to exclude trace or residual solvents resulting from the manufacture of ink components
35 prior to ink formulation.

The term "colorant", as used herein means an organic pigment or dyestuff. The energy curable liquid vehicle typically comprises one or more low molecular weight mono- or multi-functional monomers. For offset

5 inks and other inks which require higher viscosities, a resin, a reactive oligomer or polymer may also be present. The inks of the present invention may be cured thermally or by actinic radiation sources, such as electron beams and the like; or photocytically cured by
10 actinic radiation, such as UV radiation and the like, when a suitable initiating system is incorporated into the ink. The solvent-free, energy curable inks of this invention are more fully described in the following examples.

15

Pigment

The pigment is any organic pigment that can be employed for the coloration of conventional printing inks of the prior art. The pigment may also be carbon black.
20 Pigments suitable for use in the present invention may be any conventional organic pigment such as: Pigment Yellow 1, Pigment Yellow 3, Pigment Yellow 12, Pigment Yellow 13, Pigment Yellow 14, Pigment Yellow 17, Pigment Yellow 37, Pigment Yellow 63, Pigment Yellow 65, Pigment
25 Yellow 73, Pigment Yellow 74, Pigment Yellow 75, Pigment Yellow 83, Pigment Yellow 97, Pigment Yellow 98, Pigment Yellow 106, Pigment Yellow 114, Pigment Yellow 121, Pigment Yellow 126, Pigment Yellow 127, Pigment Yellow 136, Pigment Yellow 174, Pigment Yellow 176, Pigment
30 Yellow 188, Pigment Orange 5, Pigment Orange 13, Pigment Orange 16, Pigment Orange 34, Pigment Red 2, Pigment Red 9, Pigment Red 14, Pigment Red 17, Pigment Red 22, Pigment Red 23, Pigment Red 37, Pigment Red 38, Pigment Red 41, Pigment Red 42, Pigment Red 112, Pigment Red 146,
35 Pigment Red 170, Pigment Red 196, Pigment Red 210, Pigment Red 238, Pigment Blue 15, Pigment Blue 15:1, Pigment Blue 15:2, Pigment Blue 15:3, Pigment Blue 15:4, Pigment Green 7, Pigment Green 36, Pigment Violet 23, or carbon black, including Pigment Black 7 and the like.


5

Rheological Additive

The rheological additive is a polyalkylene oxide covalently bonded (i.e. grafted) to the residue of an organic colorant and has the structure $P-(U-Y)_s$, in which
 10 P is the residue of an organic colorant, Y is a polyalkylene oxide moiety containing about 4 to about 400 alkylene oxide repeat units, and U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3.

15 Typically, P is a residue of a pigment, such as, a residue of an azo pigment, phthalocyanine pigment, dioxazine pigment, quinacridone pigment, perylene pigment, perinone pigment or the like. Preferably, P is the residue of a diarylide pigment, monoazo pigment,
 20 disazo pyrazolone pigment, phthalocyanine pigment, or perylene pigment.

The polyalkylene oxide moiety, Y, may be the residue of any polyalkylene oxide such as an ethylene oxide polymer, an ethylene oxide/propylene oxide copolymer and
 25 the like. Preferably, Y is an alkylene oxide copolymer having the general formula:



30

wherein n is about 4 to about 400 and more preferably is
 35 about 4 to about 60; Q is H, CH₃ or a combination thereof; and Q' is a C₁-C₆ alkyl moiety. The weight average molecular weight of the polyalkylene oxide moiety typically is between about 300 and 3,600; and preferably between about 1,000 and 3,000. The polyalkylene oxide

5 moiety, Y, may be grafted to the residue of an organic colorant, P, through a linking moiety, U, which is preferably a covalent bond or multivalent moiety such as C₁-C₆ alkyl, -NHSO₂-, -O-, -CO-, -COC-, -N-, -CONH-, and the like. It is understood that the particular linking
10 moiety employed will be determined by those skilled in the art depending on the nature of P.

Combinations of pigment and rheological additive particularly useful in the solvent free energy curable inks of the invention are described in U.S. Patents
15 4,946,508; 4,946,509; 5,024,698; and 5,062,894; each of which is incorporated herein by reference.


In particular, Schwartz et al, U.S. Patent 4,946,508 discloses disazo pyrazolone compositions which contain said rheological additives and their method of
20 manufacture. Such disazo pyrazolone pigment compositions have the general formula:

Formula I

25

30


35



5 wherein Y is the polyalkylene oxide moiety; R¹ is H, CH₃, OCH₃, OCH₂CH₃ or Cl; n is selected from an integer from 1 to 5; R² is CH₃ or COOCH₂CH₃; R³ is H or CH₃; and X₁ is Cl or OCH₃

U.S. Patent 4,946,509, Schwartz et al discloses azomethine compositions and their method of manufacture. Such azomethine
 10 pigment compositions have the general formula:

Formula II




15

wherein Y is the polyalkylene oxide moiety containing about 4 to
 20 about 200 groups; R and R₁ are independently selected from the group consisting of H, CH₃, OCH₃, OCH₂CH₃, and Cl; n is selected from an integer from 1 to 5; X is selected from the group consisting of Cl, CH₃, OCH₃; and Z is selected from O and N-Y.

U.S. Patent 5,024,698, Schwartz et al discloses
 25 monoazomethine compositions and their method of manufacture. Such monoazomethine pigments have the general formula:

Formula III



5


wherein Y is the polyalkylene oxide moiety; R⁶ is
 10 independently selected from the group consisting of Cl,
 OCH₃, CH₃, OC₂H₅, C₂H₅, and CONH₂; R⁷ is independently
 selected from the group consisting of Cl, OCH₃, CH₃, NO₂,
 OC₂H₅, C₂H₅, CONH₂, SO₃H, OH and COOH; and a and b are
 independently selected from integers 0 to 5.

15 U.S. Patent 5,062,894, Schwartz et al discloses
 diarylide compositions and their method of manufacture.
 Such diarylide pigment compositions have the general
 formula:

Formula IV

20

25




wherein R⁴ and R⁵ are independently selected from the
 group consisting of C₁-C₄ alkyl, C₁-C₄ alkoxy, and
 30 halogen; m and p are independently selected from integers
 of 0 to 5; X² is selected from the group consisting of
 Cl, CH₃, and OCH₃; U² comprises a divalent bridging moiety
 selected from the group consisting of C₁-C₆ alkyl, -NHSO₂-,
 -O-, -CO-, -COO-, and -CONH-; Y¹ comprises the
 35 polyalkylene oxide moiety having a number average
 molecular weight of about 200 to 10,000; and k and l are
 independently selected from integers 0 or 1, with the
 proviso that for at least 50 wt.% of the composition, k
 and l are both 0, and for at least 3 wt.% of the


composition k and/or l are 1.

Other rheological additives particularly useful in the energy curable inks of this invention, include phthalocyanine compositions having the P-U-Y structure in which P, is the residue of a copper phthalocyanine pigment and wherein the linking moiety, U, is -NHSO₂- which joins P to Y. Such copper phthalocyanine based rheological additives have the general formula:

Formula V



wherein Y is a polyalkylene oxide moiety which has the general formula:



wherein n is about 4 to about 400, and a, b, c and d are integers independently from 0 to 4, provided at least one of them is 1; Q is selected from H, CH₃, or a combination thereof; and Q' is a C₁-C₆ alkyl moiety.

The rheological additive used in this invention may be prepared by any conventional method. Illustrative

5 methods for preparing the pigments with the rheological additives described herein are disclosed in U.S. Patents 4,946,508; 4,946,509; 5,024,698; and 5,062,894 and in the Examples.

The pigment compositions used in this invention
10 typically contain a minor portion of said rheological additive and a major portion of the conventional pigment. The residue of the organic colorant that is contained in the rheological additive does not need to be of the same type as the pigment of the ink formulation. For
15 example, the additive of Formula V may be utilized with Pigment Violet 23 or Pigment Black 7.

An advantage of the preparation methods disclosed in the Schwartz et al. patents supra, is that a blend of the colorant additive and the pigment is produced directly,
20 and may be used without further blending. To produce printing inks with a desired hue, a separate pigment may be added which is distinct from the pigment and rheological additive. Methods of effecting a desired hue from precursor pigments are well known to the ink
25 formulator and are illustrated in the examples.

Energy Curable Liquid Vehicle

The solvent-free, energy curable ink of this invention contains as the third essential component a
30 quantity of an energy curable liquid vehicle which is substantially free of fugitive solvent. The quantity of liquid vehicle employed is an amount sufficient to make up 100% of the ink weight when taken together with other ink components. The radiation curable liquid vehicle
35 typically comprises one or more low molecular weight mono-functional or multi-functional monomers. For offset inks and other inks which require higher viscosities, a resin, a reactive oligomer or polymer may also be present. These components may react with the monomers

5 upon curing. The energy curable liquid vehicle is characterized in that it is curable to a solid by exposure to energy from a radiant or thermal energy source as described supra. The liquid vehicle may be cured to a solid by exposure to energy, such as exposure
10 to high energy electrons from an electron beam source. Alternatively, curing of the liquid vehicle may be initiated by energy activation of a polymerization initiating system (e.g. by UV radiation) as will be described in detail hereinbelow. In this context, a
15 polymerization initiating system may be considered an optional component of the energy curable liquid vehicle. The liquid vehicle may be a ring opening polymerizable composition, a free radical addition polymerizable composition, or by a combination of ring opening and free
20 radical polymerization. In either composition, the liquid vehicle is cured or hardened by polymerizing and/or crosslinking, at least the reactive monomers of the liquid vehicle. In order to reduce environmental contamination and maintain formulation
25 integrity, the liquid vehicle is typically formulated with components having low volatility under ambient printing conditions.

When the liquid vehicle is a ring opening polymerizable composition, upon energy initiation it
30 forms a polymer typically bound by ester, or ether linkages.

In a preferred embodiment of the invention the polymerizable composition is a cationic polymerizable system comprising one or more mono-functional or multi
35 functional epoxides. The liquid vehicles typically contain at least one cycloaliphatic epoxide. Examples of such cycloaliphatic epoxides are adducts of epoxides and hydroxyl components such as glycols, polyols, or vinyl ether, such as 3,4-epoxycyclohexylmethyl 3,4-epoxy-

5 cyclohexane carboxylate; bis (3,4-epoxy-cyclohexyl-methyl)adipate; limonene monoepoxide; limonene diepoxide; diglycidyl ester of hexahydrophthalic acid; 1-vinyl-3,4-epoxycyclohexane; epoxidated dicyclopentyl alcohol; or a mixture thereof. A preferred cycloaliphatic epoxides of
10 this type is 3,4-epoxycyclohexylmethyl 3,4-epoxy-cyclohexylcarboxylate; 1,3-bis(2-(7-oxabicyclo(4.1.0)hepta-3-yl)ethyl)-1,1,3,3-tetramethyldisiloxane. In addition to the cycloaliphatic epoxides there may be one or more noncycloaliphatic epoxides, such as di- or tri-glycidyl
15 ether, alkoxylated bisphenol A, 1,6-hexane diol, glycerol; neopentylglycol; or trimethylolpropane. The epoxy diluent likewise may be diglycidyl ether of bisphenol A; an alpha-olefin epoxide, a Novalac epoxide, epoxidated linseed oil, soy oil; epoxidated
20 polybutadiene; 1,2-epoxydecane; caprolactone triol; glycidyl ether; alkyl glycidylether; epoxidated silanes; glycidoxy-methoxy silane; and glycidoxy-ethoxy silane; 2-ethylhexylglycidyl ether. In such epoxy compositions, the ink typically contains a cationic initiating system
25 activatable by actinic radiation as will be described hereinbelow. A preferred epoxy diluent is 2-ethylhexylglycidyl ether. In such epoxy compositions, the ink typically contains a cationic initiating system activatable by actinic radiation as will be described
30 hereinbelow.

When the energy curable liquid vehicle is a free radical addition polymerizable composition, the vehicle comprises a liquid compound having terminal ethylenic unsaturation.

35 Typically, the liquid vehicle is a free radical addition polymerizable system comprising an ethylenically unsaturated mono- or multi-functional monomer. The monomer is a lower molecular weight ethylenically unsaturated compound which forms a polymer directly upon

5 initiation by free radicals generated by absorbed energy.
In some formulations an oligomeric or polymeric component
which can be further polymerized may also be present. In
such cases the further polymerizable material will be
soluble in, or dispersible in the monomer vehicle.

10 Typically, the monomeric compounds have one, two, or
more terminal ethylenically unsaturated groups.

Representative of such monomeric compounds are: N-vinyl
pyrrolidinone; dipropylene glycol diacrylate;
tripropylene glycol diacrylate; butanediol diacrylate;
15 hexanediol diacrylate; trimethylol propane triacrylate;
ethoxylated trimethylol propane triacrylate; glycerol-
propoxy triacrylate; pentaerythritol triacrylate;
dipropylene glycol dimethacrylate; tripropylene glycol
dimethacrylate; butanediol dimethacrylate; hexanediol
20 dimethacrylate; trimethylol propane trimethacrylate; di-
(3-methacryloxy-2-hydroxypropyl ether) of bisphenol-A;
di(2methacryloxyethyl ether) of bisphenol-A; di-(3-
acryloxy-2-hydroxypropyl ether) of bisphenol-A; di(2-
acryloxyethyl ether) of bisphenol-A; and the like.

25 To achieve the desired ink viscosity and
crosslinking properties, typically the monomer
composition contains a combination of multifunctional
acrylic monomers along with a monomer containing a single
terminal ethylenic group, as illustrated in the examples
30 which follow.

When the inks of this invention contain an oligomeric
or polymeric material, said materials typically possess
ethylenic unsaturation which can react with the ethyl-
enically unsaturated monomers. Representative of such
35 oligomers are acrylated epoxy resins; acrylated
polyurethanes; acrylated polyesters; and the like.

The inks of the present invention may also contain a
preformed polymer such as an acrylic polymer or copolymer
of C₁-C₄ alkyl acrylates or methacrylates, or acrylic or

5 methacrylic acid, vinyl polymers and copolymers such as polyvinyl chloride, polyvinyl acetate, polyvinyl alcohol, polyvinylpyrrolidone, cellulosic polymers and copolymers; and the like.

10 Polymerization Initiating System

Unless the ink is formulated specifically for use with EB curing, it will contain a polymerization initiating system activatable by actinic radiation, such as UV or thermal radiation. Such a photoinitiator system
15 has one or more compounds that directly furnish cations or free radicals when activated by actinic radiation.

UV cationic polymerization initiating systems typically are used to initiate ring opening polymerization in systems such as the epoxy compositions
20 described herein. Such cationic initiating systems include all substances which liberate Lewis acids or Brønsted acids upon exposure to actinic radiation. Cationic photoinitiating systems which are particularly useful in the energy curable inks of this invention are
25 arylsulfonium salts, especially the triarylsulfonium salt such as triarylsulfonium phosphate, triarylsulfonium antimonate, triphenylsulfonium hexafluorophosphate, and diarylsulfonium salt; and aryl-iodonium salts, such as diaryliodonium hexafluoroantimonate,
30 bisdodecyldiphenyliodonium hexafluoroantimonate, and the like. Such cationic photoinitiators may be used individually or in combination to effect suitable curing of the ink. Preferred are diaryliodonium hexafluoroantimonate and (n⁵-2,4-cyclopentadienyl)
35 yl [(1,2,3,4,5,6-n) (1-methylethyl)benzene]-iron⁺-hexafluorophosphate(-1).

In thermal cationic polymerization initiating systems such as the thermal cationic inks described herein, a blocked acid is typically used because it does

5 not initiate the ring opening polymerization of epoxies until it is unblocked. Thermal irradiation unblocks the acid and generates a strong acid, which starts the epoxy ring opening polymerization. Some examples of "blocked" acids are Nacure TLC 1412 (King Industries), FC-122 and
10 FC-520 (Available from 3M, St. Paul, MN), and CP-66 (Available from Ciba, White Plains, NY).

Free radical polymerization initiating systems are also possible and typically require irradiation of a photoinitiator to produce free radicals that initiate
15 polymerization. A wide variety of these photoinitiators may be used in the energy curable inks of this invention. A few are described, for example, by B.M. Monroe and G.C. Weed in Photoinitiators for Free-Radical-Initiated Photo-
Imaging Systems, Chem. Rev. 93, pp. 435-48 (1993),
20 incorporated herein by reference. The reference describes the use of thioxanthone, ethyl 4-(dimethyl-amino) benzoate, alpha amino acetophenone, and Michler's ketone as photoinitiators.

25 Adjuvants

The radiation curable inks of this invention may optionally contain the usual adjuvants to adjust ink flow, surface tension, surface penetration and gloss of the cured printed ink. Such adjuvants contained in the
30 ink typically are a surface active agent, a wax, a humectant or a combination thereof. These adjuvants may function as leveling agents, wetting agents, dispersants, defrothers or deareators, or additional adjuvants may be added to provide a specific function. Preferred are
35 isopropyl adjuvants include fluorocarbon surfactants such as FC430, available from the 3M Company; silicones such as DC57, available from the Dow Chemical Corporation; polyethylene wax; polyamide wax; polytetrafluoroethylene wax; and the like.

5

Printing Ink Formulation

The solvent-free, energy curable ink contains as its essential ingredients typically about 2 to about 15 % by weight of pigment, about .1 to about 10 % by weight of rheological additive and the balance being the liquid energy curable vehicle which is substantially free of a fugitive solvent. The energy curable liquid vehicle typically comprises, one or more low molecular weight mono-functional or multi-functional monomers. For offset inks and other inks which require higher viscosities (>1,000 cps), a resin, a reactive oligomer or polymer may also be present. In addition to the essential ingredients the energy curable ink may also contain up to about 6 % by weight of polymerization initiating system activatable by actinic radiation; and up to about 10 % or less by weight of a surface active agent, a wax, humectant or combination thereof.

The primary advantage offered by the solvent-free, energy curable inks of this invention are that the rheology may be readily adjusted to provide an ink viscosity anywhere between about 8 cps to about 200 cps, preferably about 8 cps to about 20 cps (@ 240 s⁻¹ and 25°C) for the energy curable gravure inks described herein. Also, viscosities of about 3 cps to about 25 cps, preferably about 3 cps to about 15 cps (@ 240 s⁻¹ and 25°C) are achievable for the energy curable ink jet inks described herein, simply by adjusting the ratio of the various types of monomer component, and/or by adjusting the ratio of pigment and rheological additive to liquid vehicle; and/or by adjusting both ratios. The combination of pigment and rheological additive as described herein produces very fine or sub-micron pigment particle sizes that do not clog ink jet nozzles. In addition, these sub-micron particle sizes allow

5 viscosities suitable for ink jet printing to be achieved.

The ink may be prepared by any conventional mixing and milling method typically used for preparing printing inks. Typically, the pigment and rheological additive are mixed with the liquid vehicle then milled. After
10 milling additional liquid vehicle and any desirable adjuvants are optionally added and mixed to produce the energy curable ink. As indicated the above mentioned ratios are adjusted to achieve a printing ink with the desired viscosity, flow, color density, and curing
15 characteristics. The ink formulation process is more fully described in the examples.

Method of Printing and Curing

This invention is also directed to a method of
20 printing and curing an ink image comprising the steps of: preparing solvent-free energy curable inks as described supra; (b) printing the inks on a substrate surface to form an image; and (c) subjecting the image to actinic radiation or thermal energy to form a cured ink image.

25 The method is particularly directed to printing operations requiring low viscosity inks such gravure and ink jet printing. It is understood, however, that any suitable printing and curing means may be used to print and cure the solvent-free energy curable ink of
30 this invention. Such suitable means include but are not limited to flexographic printing, equipped with thermal UV and/or EB curing stations which follow the printing station. Thus when the energy curable ink is free of a photoinitiator it may be cured by actinic radiation which
35 is a beam of electrons. Alternatively, when the energy curable ink contains a polymerization initiating system, it may be cured by actinic radiation which is UV radiation. The printed energy curable ink containing a polymerization initiating system may be initially

5 subjected to UV radiation and subsequently to a beam of
electrons or thermal energy to complete the cure. As
used herein, thermal energy is intended to include
radiant energy such infrared or microwave energy and the
like; or conductive thermal energy such as that produced
10 by a heated platen or hot air oven, for example.

The following examples illustrate specific aspects of
the present invention and are not to limit the scope
thereof in any respect and should not be so construed. In
the following examples all percentages provided are in
15 volume percent unless otherwise noted.

Example 1

An energy curable, cationic ink formulation was
20 formulated using a modified Pigment Blue 15.4 composition
containing copper phthalocyanine blue pigment and
rheological additive.

A rheological additive was prepared by charging a
presscake, containing 210 parts by weight of copper
25 phthalocyanine sulfonyl chloride (which may be prepared
by any conventional method) into a mixture of 692 parts
by weight of a primary amine-terminated poly (ethylene
oxide/propylene oxide) (5/95) copolymer having a number
average molecular weight of approximately 2,000
30 (available as XTJ 507 from the Huntsman Corporation) and
66 parts by weight of sodium carbonate and mixed. The
final reaction mixture was then heated to 80-90°C under
vacuum to remove water and produce the copper
phthalocyanine additive.

35 The modified Pigment Blue 15.4 composition was
prepared by combining 12 % by weight of the copper
phthalocyanine derived rheological additive where P is
the residue of copper phthalocyanine with 79% by weight
of conventional Pigment Blue 15.4 during the attrition

5 process step of the conventional pigment.

The energy curable, cationic ink was formulated from the following components.

	<u>COMPONENTS</u>	<u>WEIGHT %</u>
10	Cyracure® 6110 ^(a)	15
	Modified Pigment Blue 15.4	5
	CD 1012 ^(b)	2
	Irgacure® 261 ^(f)	.5
	DVE 3 ^(g)	76
15	PE wax ^(d)	1
	DC 57 ^(e)	.5

-
- (a) Cyracure® 6110, available from the Union Carbide Corporation, Boundbrook, NJ is 3,4-epoxycyclohexylmethyl-3,4-epoxycyclohexylcarboxylate;
- 20 (b) CD 1012, available from the Sartomer Corporation, Exton, PA, is diaryliodonium of hexafluoroantimonate;
- (d) PE wax, available from the Shamrock Corporation, Newark, NJ is polyethylene wax; and
- 25 (e) DC 57, available from the Dow Chemical Corporation, Midland, MI, is silicone additive.
- (f) Irgacure® 261, available from the Ciba Corporation, White Plains, NY, is {N³-2,4-cyclopentadien-1-yl}[(1,2,3,4,5,6-N)(1-methyl ethyl)benzene I-iron-hexafluorophosphate; and
- 30 (g) DVE, available from the GAF Corporation, is triethyleneglycol divinyl ether.
-

The Cyracure® 6110 and the modified Pigment Blue 15.4 were mixed at high speed (about 2000 rpm) with a Cowles blade and then processed through a media mill containing 1 mm size media. After processing, the remaining components were added and the viscosity of the two inks were measured.

	<u>PIGMENT</u>	<u>VISCOSITY @ 25°C</u>
40	Modified PB-15.4	20±5 cps at 240 s-1
	Conventional PB-15.4	100±20 cps at 240 s-1

Printing runs were carried out with a gravure hand-proofer (available from Pamarco Inc.) The major elements of the gravure hand-proofer are: a 300 line/inch (118

5 line/cm) anilox roller; and a doctor blade assembly for regulating the ink supplied to the anilox roller. The printed samples were passed through a UV curing unit, (available from R.P.G. Industries) having a lamp with an output of 400 Watts/inch in the UV spectral region and a
10 cylindrical reflector. The substrate which was printed was the polyester label film from Fasson. The printing speed was about 1 m/sec (200 ft/min) Using modified Pigment Blue 15.4 ink composition, a uniform ink film was applied to the substrate with the hand proofer and cured
15 with this curing unit. A cured uniform ink film was likewise printed using conventional Pigment Blue 15.4 ink composition.

Color density and gloss measurements as described in Example 1 were carried out with the modified and the
20 conventional Pigment Blue 15.4 prints. The assessed quality using the two ink formulations were:

<u>PIGMENT</u>	<u>COLOR DENSITY</u>	<u>GLOSS 60°</u>
Modified PB-15.4	1.4	90
25 Conventional PB-15.4	1.1	70

The ink containing modified Pigment Blue 15.4 demonstrates more uniform lay and less reticulation than the ink containing the conventional pigment, which
30 results in higher density and better gloss of the print.

Example 2

An energy curable, cationic ink formulation was
35 formulated using a modified Pigment Violet 23 composition containing Pigment Violet 23 and rheological additive.

Modified Pigment Violet 23 composition was prepared by combining 15 % by weight of the copper phthalocyanine derived rheological additive of Example 1 with 85% by

5 weight of conventional Pigment Violet 23 during the attrition process step of the conventional pigment.

The energy curable, cationic ink was formulated from the following components.

	<u>COMPONENTS</u>	<u>WEIGHT %</u>
10	Cyracure® 6110	26
	Modified Pigment Violet 23	8
	E6250	60
	CD 1012	5
	PE wax	1
15	DC 57	.5

(h) E6250, available from the Huls America Corporation, Somerset, NJ, is (2-(3,4-epoxycyclo hexyl)ethyltrimethoxysilane).

20 The Cyracure® 6110 and the modified Pigment Violet 23 were mixed at high speed (about 1000 rpm) with a Cowles blade and then processed through a media mill containing 1 rvm size media. After Processing the remaining components were added and the viscosity of the two inks
25 were measured.

<u>PIGMENT</u>	<u>VISCOSITY @ 25°C</u>
Modified PV-23	20±5 cps at 240 s ⁻¹
Conventional PV-23	150±50 cps at 240 s ⁻¹

30

Printing runs, as describe in Example 1, were carried out with the modified Pigment Violet 23 and compared to conventional Pigment Violet 23. Color density and gloss measurements were carried out with the modified and
35 conventional Pigment Violet 23 prints. The assessed quality using the two ink formulations were:

	<u>PIGMENT</u>	<u>COLOR DENSITY</u>	<u>GLOSS 60°</u>
	Modified PV-23	2.34	75
40	Conventional PV-23	1.88	46

5

Example 3

A UV curable ink jet ink was formulated using a
10 modified Pigment Black 7 composition, prepared by dry
mixing 19 wt.% of copper phthalocyanine rheological
additive as described in Example 1 and 81 wt.% of a
conventional Black Pigment 7 and adding the following
components:

15

<u>Components</u>	<u>Weight %</u>
Cyracure [®] 6105 ^(a)	15
Modified Pigment Black 7	5
Limonene Dioxide	75
20 UVI 6974 ^(b)	5

(a) Cyracure 6105, available from the Union Carbide
Corporation, is 3,4epoxycyclohexylmethyl-3, 4
epoxycyclohexylcarboxylate; and

25

(b) UVI 6974, available from the Union Carbide Corporation, is
triarylsulphonium hexafluoroantimonate.

The Cyracure 6105 and the modified Pigment Black 7
were mixed together in a ratio of 3:1. After processing,
30 the remaining components were added slowly at low mixing
speed. The resulting ink was subjected to a set of
physical tests, i.e. viscosity measurements at 25°C and
100 s⁻¹, a thermal stability test and optical microscopy
for pigment dispersion. The thermal stability test
35 consists of a rheological profile (viscosity vs. time) of
the ink, obtained by shearing the sample constantly at
100 s⁻¹ and at temperatures from 25°C to 80°C and back to
25°C. If the viscosity-temperature profile on the upward
curve and the downward curve match exactly, thermal
40 stability is good. Any other behavior is an indication
of irreversible pigment flocculation.

The 25°C viscosity at 100 s⁻¹ was 14 mpa.s, which is

5 fine for several ink jet heads. The thermal stability was good. Optical microscopy showed a very fine dispersion with no particles above one micron.

A draw down was done on coated paper, aluminum foil and on a corona treated polyethylene film, with a #3
10 Meyer Rod. The resulting ink lays were cured at 200 fpm, with 2 lamps having an output of 300 Watts/inch in the UV spectral region and a cylindrical reflector. The ink layers were fully cured and exhibited good adhesion on both substrates, good resistance to water and good
15 scratch resistance.

The ink jet ink was filled in the DOD printer head and jetted at room temperature onto a coated paper, a film and aluminum foil. The ink jetted fine and dot addressability was excellent. The resulting printed
20 substrates were cured under the same conditions as the draw downs and exhibited the same resistance properties.

Example 4

25 A UV curable ink jet ink formulation was formulated using a modified Pigment Blue 15:4 composition prepared by according to Example 1. The following components were then added:

30	<u>Components</u>	<u>Weight %</u>
	Cyracure [®] 6105 ^(a)	11.9
	Modified Pigment Phthalocyanine Blue 15:4	5.1
	Limonene Dioxide	78
	UVI 6974 ^(b)	15

35 -----
(a) Cyracure 6105, available from the Union Carbide Corporation, is 3,4epoxycyclohexylmethyl-3, 4 epoxycyclohexylcarboxylate; and
(b) UVI 6974, available from the Union Carbide Corporation, is
40 triarylsulphonium hexafluoroantimonate.

5 The Cyracure 6105 and the modified Pigment
Phthalocyanine Blue 15:4 were mixed together in a ratio
of 7:3. After processing, the remaining components were
added slowly at low mixing speed. The resulting ink was
subjected to the same set of physical tests as in Example
10 3.

The 25°C viscosity at 100 s⁻¹ was 13 mPa.s, which is
fine for several ink jet heads. The thermal stability
was good. Optical microscopy showed a very fine
dispersion with no particles above one micron.

15 Draw downs were done on aluminum foil, corona
treated polyethylene and polypropylene films, a
chemically treated polyester film, a PVDC coated
cellophane and on metallized polypropylene film, with a
#3 Meyer Rod. The ink lays were cured at 200 fpm, with 2
20 lamps having an output of 300 Watts/inch in the UV
spectral region and a cylindrical reflector. The cured
ink lays exhibited good adhesion on every substrate cited
except on chemically treated polyester film, good
resistance to water on every substrate except on corona
25 treated polyethylene film and good scratch resistance on
every substrate except on metallized polypropylene film.

Example 5

30 A UV curable ink jet ink formulation was formulated
using a modified Pigment Black 7 composition as described
in Example 3, and the following components:

<u>Components</u>	<u>Weight %</u>
Siloxane S-200 ^(a)	14
35 Modified Pigment Black 7	6
Z-6040 ^(b)	75
UVI 6974 ^(c)	5

40 (a) Siloxane S-200, experimental product available from Rhone-
Poulenc, Cranbury, NJ, 1,3Bis(2-(7-oxabicyclo(4.1.0) hept-3-

- 5 yl)ethyl)-1,1,3,3-tetramethyldisiloxane;
(b) Z-6040, available from Dow Corning, Midland, MI, is
glycidoxymethoxy silane; and
(c) UVI 6974, available from the Union Carbide Corporation, is
triarylsulphonium hexafluoroantimonate.

10 -----
The Siloxane S-200 and the modified Pigment Black 7
were mixed together in a ratio of 4:6. After processing,
the remaining components were added slowly at a low
mixing speed. The resulting ink was subjected to the
15 same set of physical tests as in Example 3.

The 25°C viscosity at 100 s⁻¹ was 5 mPa.s, which is
fine for several ink jet heads. The thermal stability
was good. Optical microscopy showed a very fine
dispersion with no particles above one micron.

20 Draw downs were done on aluminum foil, corona
treated polyethylene and polypropylene films, a
chemically treated polyester film, a PVDC coated
cellophane and on metallized polypropylene film, with a
#3 Meyer Rod. The resulting ink lays were cured at 200
25 fpm, with 2 lamps having an output of 300 Watts/inch in
the UV spectral region and a cylindrical reflectors. The
cured ink lays exhibited good adhesion on every substrate
cited above except on chemically treated polyester film,
good resistance to water on every substrate except on
30 metallized polypropylene film where it was fair, and good
scratch resistance on every substrate except on
metallized polypropylene film where it was fair.

The ink jet ink was filled in the DOD printer head
and jetted at room temperature onto a coated paper, a
35 film and aluminum foil. The ink jetted fine and dot
addressability was excellent. The resulting printed
substrates were cured under the same conditions as the
draw downs and exhibited the same resistance properties.

Example 6

A UV curable ink jet ink formulation was formulated using a modified Pigment Black 7 composition as described in Example 3, and the following components:

<u>Components</u>	<u>Weight %</u>
Cyracure [®] 6105 ^(a)	18.6
Modified Pigment Black 7	5.9
Z-6040 ^(b)	70.5
UVI 6974 ^(c)	5

(a) Cyracure 6105, available from the Union Carbide Corporation, is 3,4epoxycyclohexylmethyl-3, 4 epoxycyclohexylcarboxylate;

(b) Z-6040, available from Dow Corning, is glycidoxymethoxy silane; and

(c) UVI 6974, available from the Union Carbide Corporation, is triarylsulphonium hexafluoroantimonate.

The Cyracure 6105 and the modified Pigment Black 7 were mixed together in a ratio of 4:6. After processing, the remaining components were added slowly at slow mixing speed. The resulting ink was subjected to the same set of physical tests as in Example 3.

The 25°C viscosity at 100 s⁻¹ was 8.5 mpa.s, which is fine for several Ink Jet heads. The thermal stability was good. Optical microscopy showed a very fine dispersion with no particles above one micron.

Draw downs were done on aluminum foil, corona treated polyethylene atid polypropylene films, a chemically treated polyester film, a PVDC coated cellophane and on metallized polypropylene film, with #3 Meyer Rod. The resulting ink lays were cured at 140 fpm, with 2 lamps having an output of 300 Watts/inch in the UV spectral region and a cylindrical reflector. The cured ink lays exhibited good adhesion on every substrate cited above except on chemically treated polyester film where it was poor, good resistance to water on every substrate

except on metallized polypropylene film where it was fair to poor, and good scratch resistance on every substrate except on metallized polypropylene film where it was fair to poor.

Example 7

A UV curable ink jet ink formulation was formulated using a modified pigment Black 7 composition as described in Example 3, and the following components:

Components	Weight %
Flexol [®] LOE ^(a)	9.5
ERLX 4683 ^(b)	1.7
Modified Pigment Black 7	4.8
Limonene Dioxide	39
Z-6041 ^(c)	40
UVI 6974 ^(d)	5

(a) Flexol LOE, available from the Union Carbide Corporation, is an epoxidized linseed Oil (oxobis (1-butane-2, 2-dimethylol));

(b) ERLX 4683 is an experimental product available from the Union Carbide Corporation and is tetrakis (3,4-epoxycyclohexane-carboxylate); and

(c) Z-6041 is an experimental product available from Dow Corning and is glycidoxy-ethoxy silane; and (d) UVI 6974, available from the Union Carbide Corporation, is triarylsulphonium hexafluoroantimonate.

The Flexol LOE, the ERLX 4683 and the modified Pigment Black 7 were mixed together in a ratio of 20 parts of Flexol LOE, 3.5 parts of ERLX 4683 and 10 parts of modified Pigment Black 7. After processing, the remaining components were added slowly at low mixing speed. The resulting ink was subjected to the same set of physical tests as in Example 3.

The 25°C viscosity at 100 s⁻¹ was 7.5 mpa.s, which is fine for several ink jet heads. The thermal stability was good. Optical microscopy showed a very fine

5 dispersion with no particles above one micron.

Draw downs were done on aluminum foil and corona treated polyethylene with a #3 Meyer Rod. The resulting ink lays were cured at 200 fpm, with 2 lamps having an output of 300 Watts/inch in the UV spectral region and a
10 cylindrical reflector. The cured ink lays exhibited good adhesion, good resistance to water and good scratch resistance on both substrates.

Example 8

15

A UV curable ink jet ink formulation was formulated using a modified Pigment Yellow 12 composition. The modified Pigment Yellow 12 composition containing Pigment Yellow 12 and rheological additive was prepared as
20 described in Example III of U.S. Patent 5,062,894. A mixture of 16.5 parts of isatoic anhydride (96% pure) and 220 parts of a primary amine-terminated poly (ethylene oxide/propylene oxide) (70/30) copolymer having a number average molecular weight of approximately 2,000
25 (available from Huntsman Corporation) was stirred and heated gradually to 80°C until evolution of CO₂ ceased. The infrared spectrum indicated that the isatoic anhydride had completely reacted as evidenced by the disappearance of the characteristic anhydride absorptions
30 at 1748 cm⁻¹. Thereafter, 16.5 parts of t-butyl acetoacetate were added and the reaction mixture was heated at 95°C and stirred for 8 hours to form Agent 1.

Tetrazotized 3,3' O-dichlorobenzidine (DCB) was then prepared by adding 21.7 parts DCB to 39.8 parts of 200 Be
35 hydrochloric acid and 140 parts of ice/water mixture with constant stirring to form a homogenous suspension. 32.6 parts of a 38% solution of sodium nitrite was added to the suspension and stirring was continued for 1 hour 0-3°C. The excess nitrous acid was then destroyed by the

5 addition of approximately 0.5 part sulfamic acid.

A fine suspension of coupler was prepared by charging 31.1 parts acetoacetanilide and 0.5 part phenylmethyl pyrazolone (a shading agent) to 400 parts water and 33.6 parts of 50% sodium hydroxide. The mixture was stirred until all solids were dissolved, then the temperature was adjusted between 0 and 5°C and thereafter the coupler was precipitated by slowly adding 36.2 parts of 70% acetic acid. Immediately prior to coupling, 20.6 parts of Agent 1 were added to the coupler suspension as stirring was maintained throughout coupler preparation and reaction.

Coupling was then carried out by adding the solution of tetrazotized DCB to the fine suspension of coupler over a 40 minute period while stirring until no excess tetrazotized DCB remained. Then the temperature was increased to 40°C. The resulting pigment slurry was stirred an additional 30 minutes, filtered, washed and dried in an oven at 75°C. (Yield 69 parts of Modified Pigment Yellow 12 composition containing Pigment Yellow 12 and rheological additive). The following components were added:

<u>Components</u>	<u>Weight %</u>
Cyracure [®] 6105 ^(a)	30
Modified pigment Yellow 12	5
30 Z-6040 ^(b)	60
UVI 6974 ^(c)	5

(a) Cyracure 6105, available from the Union Carbide Corporation, is 3,4epoxycyclohexylmethyl-3, 4 epoxycyclohexylcarboxylate;

(b) Z-6040, available from Dow Corning, is glycidoxymethoxy silane;

(c) UVI 6974, available from the Union Carbide Corporation, is triaryl-sulphonium hexafluoroantimonate.

The Cyracure 6105 and the modified Pigment Yellow 12 were mixed together in a ratio of 3:1. After processing, the remaining components were added slowly at low mixing

5 speed. The resulting ink was subjected to the same set of physical tests as in Example 3.

The 25°C viscosity at 100 s⁻¹ was 12 mpa.s, which is fine for several Ink Jet heads. The thermal stability was good up to 50°C. Optical microscopy showed a very
10 fine dispersion with no particles above one micron.

Draw downs were done on aluminum foil and corona treated liolyethylene with a #3 Meyer Rod. The resulting ink lays were cured at 200 fpm, with 2 lamps having an output of 300 Watts/inch in the UV spectral region and a
15 cylindrical reflector. The cured ink lays exhibited good adhesion, good resistance to water and good scratch resistance on both substrates.

Example 9

20

A thermal curable ink jet ink formulation was formulated using a modified Pigment Black 7 composition according to Example 3, and the following components:

25	<u>Components</u>	<u>Weight %</u>
	Cyracure [®] 6105 ^(a)	14
	Modified Pigment Black 7	6
	Limonene Dioxide	75
	TLC 14-12 ^(b)	2.5
30	Propylene Carbonate	2.5

(a) Cyracure 6105, available from the Union Carbide Corporation, is 3,4epoxycyclohexylmethyl-3, 4 epoxycyclohexylcarboxylate; and

35 (b) TLC 14-12, experimental product available from King Industries, is a blocked acid.

The Cyracure 6105 and the modified Pigment Black 7 were mixed together in a ratio of 3:1. The thermal
40 initiator, TLC 14-12, was dissolved in Propylene Carbonate in a ratio of 1:1. After processing, the Limonene Dioxide was added slowly at low mixing speed,

5 followed shortly by the addition of the thermal initiator solution. The resulting ink was subjected to the same set of physical tests as in Example 3, except the thermal stability test.

10 The 25°C viscosity at 100 s⁻¹ was 14 mPa.s, which is fine for several ink jet heads. Optical microscopy showed a very fine dispersion with no particles above one micron.

Draw downs were done on aluminum foil and on coated paper with a #3 Meyer Rod. The resulting ink lays were 15 cured in an oven at 140°C for 45 s or 160°C for 15 s. The cured ink lays exhibited good adhesion, good resistance to water and good scratch resistance on both substrates.

The ink jet ink was filled in the DOD printer head and jetted at room temperature onto a coated paper, a 20 film and aluminum foil. The ink jetted fine and dot addressability was excellent. The resulting printed substrates were cured under the same conditions as the draw downs and exhibited the same resistance properties.

25 Example 10

A thermal curable ink jet ink formulation was formulated using a modified Pigment Black 7 composition according to Example 3, and the following components:

30

<u>Components</u>	<u>Weight %</u>
Cyracure® 6105 (a)	14
Modified Pigment Black 7	6
Limonene Dioxide	75
35 FC-520 (b)	5

(a) Cyracure 6105, available from the Union Carbide Corporation, is 3,4epoxycyclohexylmethyl-3, 4 epoxy-

40 (b) FC-520, available from 3M, St. Paul, MN, is a blocked fluoroaliphatic acid salt.

5 -----
The Cyracure 6105 and the modified pigment black 7
were mixed together in a ratio of 3:1. After processing,
the Limonene Dioxide was added slowly at low mixing
speed, followed shortly by the addition of the FC-520
10 thermal initiator. The resulting ink was subjected to
physical testing. The 25°C viscosity at 100 s⁻¹ was 14
mpa.s, which is fine for several ink jet heads. Optical
microscopy showed a very fine dispersion with no
particles above one micron.

15 Draw downs were done on aluminum foil and on coated
paper with a #3 Meyer Rod. The resulting ink lays were
cured in an oven at 140 °C for 60 s or 160 °C for 30 s.
The cured ink lays exhibited good adhesion, good
resistance to water and good scratch resistance on both
20 substrates.

Example 11

A thermal curable ink jet ink formulation was
25 formulated using a modified Pigment Black 7 composition
according to Example 3, and the following components:

<u>Components</u>	<u>Weight %</u>
Cyracure [®] 6105 ^(a)	24
30 Modified Pigment Black 7	6
Z-6040 ^(b)	65
TLC 14-12 ^(c)	2.5
Propylene Carbonate	2.5

35 -----
(a)Cyracure 6105, available from the Union Carbide
Corporation, is 3,4epoxycyclohexylmethyl-3, 4 epoxy-
cyclohexylcarboxylate;

(b) Z-6040, available from Dow Corning, is glycidoxy-methoxy
silane; and

40 (c)TLC 1412, experimental product available from King
Industries, is a blocked acid.

The Cyracure 6105 and the modified Pigment Black 7

5 were mixed together in a ratio of 4:6. The thermal initiator, TLC 1412, was dissolved in propylene carbonate in a ratio of 1:1. After processing, the remaining
Cyracure 6105 and the Z-6040 were added slowly added at low mixing speed, followed shortly by the addition of the
10 thermal initiator solution. The resulting ink was subjected to physical testing. The 25°C viscosity at 100 s⁻¹ was 10 mpa.s, which is fine for several Ink Jet heads. Optical microscopy showed a very fine dispersion with no particles above one micron.

15 Draw downs were done on aluminum foil and on coated paper with a #3 Meyer Rod. The resulting ink lays were cured in an oven at 160°C for 15 s. The cured ink lays exhibited good adhesion, good resistance to water and good scratch resistance on both substrates.

20

Example 12

A thermal curable ink jet ink formulation was formulated using a modified Pigment Black 7 composition
25 according to Example 3, and the following components:

<u>Components</u>	<u>Weight %</u>
Siloxane S-200 ^(a)	14
Modified Pigment Black 7	6
30 Z-6040 ^(b)	75
TLC 14-12 ^(c)	2.5
Propylene Carbonate	2.5

35 (a) Siloxane S-200 experimental product available from Rhone-Poulenc, 1,3Bis(2-(7-oxabicyclo(4.1.0) hept-3-yl)ethyl)-1,1,3,3-tetramethyldisiloxane;

(b) Z-6040, available from Dow Corning, is glycidoxymethoxysilane; and

40 (c) TLC 1412, experimental product available from King Industries, is a blocked acid.

The Silane S-200 and the modified Pigment Black 7 were mixed together in a ratio of 4:6. The thermal

5 initiator, TLC 14-12, was dissolved in Propylene
Carbonate in a ratio of 1:1. After processing, the
remaining Cyacure 6105 and the Z-6040 were added slowly
at low mixing speed, followed shortly by the addition of
the thermal initiator solution. The resulting ink was
10 subjected to physical testing. The 25°C viscosity at 100
s⁻¹ was 5 mPa.s, which is fine for several ink jet heads.
Optical microscopy showed a very fine dispersion with no
particles above one micron.

Draw downs were done on aluminum foil and on coated
15 paper with #3 Meyer Rod. The resulting ink lays were
cured in an oven at 160°C for 15 s. The cured ink lays
exhibited good adhesion, good resistance to water and
good scratch resistance on both substrates.

The ink was filled in the DOD printer head and jetted
20 at room temperature onto a coated paper and aluminum
foil. The ink jetted fine and dot addressability was
excellent.

Tables I, II and III summarize the formulations and
resulting physical properties for ink jet inks prepared
25 according to a few Examples and other ink jet inks
prepared in accordance with the present invention. The
inks were jetted onto coated paper substrates.

TABLE I

Component - Description			Supplier		Examples						
			13	6	3	4	7	14			
Modified Black	Pigment	Sun Chemical	6.0	5.9	5.0		4.8	4.8			
Modified Blue	Pigment	Sun Chemical				5.1					
Cyarcure 6105	Di-Cyclo-Aliphatic Epoxy	Union Carbide	14.0	18.6	15.0	11.9					
LOO	Limonene Dioxide	Elf Atochem			75.0	78.0	39.0	79.0			
Z-6040	Glycidoxy-methoxy silane	Dow Corning	75.0	70.5							
Z-6041	Glycidoxy-ethoxy silane	Dow Corning					40.0				
Flexol LOE	Epoxidized Linseed Oil	Union Carbide					9.5	9.5			
	Oxobis(1-butane-2,2-dimethylol)										
ERLX 4683	Tetrakis(3,4-epoxycyclohexane-carboxylate)	Union Carbide					1.7	1.7			
UVI 6974	Tri-aryl Sulphonium Hexafluoro-Antimonate Salt	Union Carbide	5.0	5.0	5.0	5.0	5.0	5.0			
	(Total)		100.0	100.0	100.0	100.0	100.0	100.0			
Physical Property Data											
Curing Speed (µm) on coated paper, with 2 lamps 300 Watts			>100	>100	>200	>200	>200	>200			
Viscosity 25°C, 100 s-1 (cps)			6.8	8.5	14	13	7.5	11			
Thermal Stability (°C)			>80	>80	>80	>80	>80	>80			
Jettability					Excel.						
Pigment dispersion (Optical Microscopy)			V. Good	V. Good	V. Good	V. Good	V. Good	V. Good	V. Good		

TABLE II

Component	Description	Supplier	Examples									
			15	16	17	8	5	18	19			
Modified Black	Pigment	Sun Chemical	10.8		6.0		6.0		6.0			6.0
Modified Yellow	Pigment	Sun Chemical		4.0		5.0						
Modified Blue	Pigment	Sun Chemical										
Cyarcure 6105	Di-Cyclo-Aliphatic Epoxy	Union Carbide	7.2	12.0	24.0	30.0						
LDO	Limonene Dioxide	Elf Atochem	77.0	79.6	65.0							
Z-6040	Glycidoxy-methoxy silane	Dow Corning				60.0	75.0	60.0	80.0			
Siloxane S-200	1,3-Bis(2-(7-oxabicyclo(4,1,0) hept-3-yl)ethyl)-1,1,3,3-tetramethyldisiloxane	Rhone Poulenc					14.0	29.0	9.0			
BYK 361	Surfactant	BYK Chemie		0.4								
UVI 6974	Triaryl Sulphonium Hexafluoro-Antimonate Salt	Union Carbide	5.0	4.0	5.0	5.0	5.0	5.0	5.0			
Physical Property Data			100.0	100.0	100.0	100.0	100.0	100.0	100.0			
(Total)												
Curing Speed (fpm) on coated paper, with 2 lamps 300 Watts			>200	>200	>200	>200	>100	>100	>100			
Viscosity @ 25°C, 100 s-1 (cps)			18	17	13	12	5		4			
Surface Tension (mN/m)			35.5	34	34.9							
Thermal Stability (°C)			> 80	38	> 80	52	>80	>80	>80			
Jettability							Excel.					
Pigment dispersion (Optical Microscopy)			V. Good	Good	V. Good	V. Good	V. Good	V. Good	V. Good			

TABLE III

Component	Description	Supplier	Examples					
			10	9	11	12		
High Perf. Black 7	Pigment	Sun Chemical	6.0	6.0	6.0	6.0		
Cyarcure 6105	Di-Cyclo-Aliphatic Epoxy	Union Carbide	14.0	14.0	24.0			
LDO	Limonene Dioxide	Elf Atochem	75.0	75.0				
Z-6040	Glycidoxy-methoxy	Dow Corning			65.0	75.0		
Siloxane S-200	1,3-Bis(2-(7-oxabicyclo(4.1.0)hept-3-yl)ethyl)-1,1,3,3-tetramethyldisiloxane	Rhone Poulenc				14.0		
TLC-1412	Sulphonium Salt	King		2.5	2.5	2.5		
Propylene Carbonate	Propylene Carbonate	Texaco		2.5	2.5	2.5		
FC-520	Fluoroaliphatic acid salt	3M	5.0					
	(Total)		100.0	100.0	100.0	100.0		
Physical Property Data								
Curing Temperature (°C)			160	140	160	160		
Curing time (s)			30	30	15	60		
Viscosity 25°C, 100 s ⁻¹ (cps)			-	-	10	5		
Jetability			-	-	-	Excel		
Pigment dispersion (Optical Microscopy)			V. Good	V. Good	V. Good	V. Good		

5

Those skilled in the art having the benefit of the teachings of the present invention as hereinabove set forth, can effect numerous modifications thereto. These modifications are to be construed as being encompassed
10 within the scope of the present invention as set forth in the appended claims.

5 What is claimed is:

1. An energy curable gravure ink comprising: a pigment; a rheological additive having the structure:


10 P-(U-Y)_s

wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P, and s is an integer from 1 to
15 3 and; an energy curable liquid vehicle; wherein the ink is substantially free of fugitive solvent and has a viscosity ranging from about 8 cps to about 200 cps.

2. The ink of claim 1 wherein the polyalkylene oxide moiety is an ethylene oxide polymer.

20 3. The ink of claim 1 wherein the polyalkylene oxide moiety is an ethylene oxide/propylene oxide copolymer.

4. The ink of claim 3 wherein the copolymer has the general formula:



wherein n is about 4 to about 400; Q is H, CH₃, or a
30 combination thereof; and Q' is a C₁-C₆ alkyl moiety.

35


5 5. The ink of claim 4 wherein n is about 4 to 35 about 60.

6. The ink of claim 1 wherein P is a residue of an azo pigment, phthalocyanine pigment, dioxazine pigment, quinacridone pigment, perylene pigment, or perinone pigment.

7. The ink of claim 1 wherein U is a covalent bond, or a multivalent moiety selected from the group consisting of C₁-C₆ alkyl, -NHSO₂-, -O-, -CO-, -COO-, -N=, and -CONH-.


15 8. The ink of claim 1 where s has the value 1 or 2.

9. The ink of claim 1 wherein the rheological additive is an azomethine having the general formula:




wherein Y is the alkylene oxide polymer containing about
30 to about 200 groups; R and R¹ are independently selected from the group consisting of H, CH₃, OCH₃, OCH₂CH₃, and Cl; n is an integer from 1 to 5; X is selected from the group consisting of C₁, CH₃, and OCH₃; and Z is selected from the group consisting of O and N-Y.

35 10. The ink of claim 1 wherein the additive is an azomethine having the general formula:



wherein Y is the polyalkylene oxide polymer containing about 4 to about 20 repeat units; R¹ is H, CH₃, OCH₃, OCH₂CH₃, or Cl; n is an integer from 1 to 5; R₂ is CH₃ or COOCH₂CH₃; R³ is H or CH₃; and X₁ is Cl or OCH₃.


11. The ink of claim 1 wherein the additive is a diarylide having the general formula:



wherein: R⁴ and R⁵ are independently selected from the group consisting of C₁-C₄ - alkyl, C₁-C₄ alkoxy, and halogen; m and p are independently integers of 0 to 5; X² is selected from the group consisting of C₁, CH₃, and OCH₃; U² comprises a divalent bridging moiety selected from the group consisting of C₁-C₆ alkyl, -NHSO₂-, -O-, -CO-, -COO-, and -CONH-; Y¹ comprises the polyalkylene oxide moiety having a number average molecular weight of about 200 to 10,000; and k and l are independently integers of 0 or 1, with the proviso that for at least 50 wt.% of the pigment composition, k and l are both equal


to 0, and for at least 3 wt.% of the pigment composition
5 k and/or 1 are equal to 1.

12. The ink of claim 1 wherein the additive is an
azomethine having the general formula:




wherein Y is the polyalkylene oxide polymer containing
about 4 to about 20 repeat units; R6 is independently
20 selected from the group consisting of Cl, OCH₃, CH₃,
OC₂H₅, C₂H₅, and CONH₂; R⁷ is independently selected from
the group consisting of Cl, OCH₃, CH₃, NO₂, OC₂H₅, C₂H₅,
CONH₂, SO₃H, OH and COOH; and a and b are independently
integers of 0 to 5.

25 13. The ink of claim 1 wherein the additive is a
phthalocyanine having the general formula:



wherein Y has the general formula:



5 to wherein n is about 4 to about 400, and a, b, c and d are integers independently from about 0 to about 4, provided at least one of them is 1; Q is H, CH₃ or a combination thereof; and Q' is a C₁-C₆ alkyl moiety.

14. The ink of claim 1 wherein the pigment is
10 selected from the group consisting of Pigment Yellow 1, Pigment Yellow 3, Pigment Yellow 12, Pigment Yellow 13, Pigment Yellow 14, Pigment Yellow 17, Pigment Yellow 37, Pigment Yellow 63, Pigment Yellow 65, Pigment Yellow 73, Pigment Yellow 74, Pigment Yellow 75,
15 Pigment Yellow 83, Pigment Yellow 97, Pigment Yellow 98, Pigment Yellow 106, Pigment Yellow 114, Pigment Yellow 121, Pigment Yellow 126, Pigment Yellow 127, Pigment Yellow 136, Pigment Yellow 174, Pigment Yellow 176, Pigment Yellow 188, Pigment Orange 5, Pigment Orange 13,
20 Pigment Orange 16, Pigment Orange 34, Pigment Red 2, Pigment Red 9, Pigment Red 14, Pigment Red 17, Pigment Red 22, Pigment Red 23, Pigment Red 37, Pigment Red 38, Pigment Red 41, Pigment Red 42, Pigment Red 112, Pigment Red 146, Pigment Red 170, Pigment Red 196, Pigment Red
25 210, Pigment Red 238, Pigment Blue 15, Pigment Blue 15:1, Pigment Blue 15:2, Pigment Blue 15:3, Pigment Blue 15:4, Pigment Green 7, Pigment Green 36, Pigment Violet 23, and Pigment Black 7.

15. The ink of claim 1 wherein the pigment is
30 distinct from P.

16. The ink of claim 1 wherein the pigment is the same as P.

17. The ink of claim 16 wherein the ink contains an additional distinct pigment.

35 18. The ink of claim 1 wherein the energy curable liquid vehicle is a ring opening polymerizable composition.

19. The ink of claim 18 wherein the polymerizable composition is a cationic polymerizable system comprising

5 one or more mono-functional and/or multi-functional epoxide monomers.

20. The ink of claim 19 wherein the cationic polymerizable composition comprises a cycloaliphatic epoxide.

10 21. The ink of claim 20 wherein the cycloaliphatic epoxide is selected from 3,4-epoxycyclohexylmethyl 3,4-epoxycyclohexylcarboxylate and 1,3-bis(2-(7-oxabicyclo(4.1.0)hepta-3-yl)ethyl)-1,1,3,3-tetramethyl-disiloxane.

15 22. The ink of claim 19 wherein the cationic polymerizable composition comprises a non-cycloaliphatic epoxide.

23. The ink of claim 22 wherein the non-cycloaliphatic epoxide is selected from glycidoxy-methoxy
20 silane and glycidoxy-ethoxy silane.

24. The ink of claim 18 further comprising a polymerization initiating system activatable by actinic radiation.

25 25. The ink of claim 24 wherein the polymerization initiating system employs a thermal and cationic initiator.

26. The ink of claim 1 wherein the energy curable liquid vehicle is a free radical addition polymerizable system comprising an ethylenically unsaturated
30 monofunctional or multi-functional monomer.


27. The ink of claim 26 wherein the ink contains a free radical generating, addition polymerization initiating system activatable by actinic radiation.

28. The ink of claim 1 wherein the ink contains a
35 surface active agent, a wax, or a combination thereof.

29. A method of gravure printing and curing a gravure ink comprising the steps of:

(a) preparing an energy curable gravure ink having a pigment and a rheological additive of the

5 structure:



wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety
10 covalently bonding Y to P, and s is an integer from 1 to 3; and an energy curable liquid vehicle; wherein the ink is substantially free of fugitive solvent and has a viscosity ranging from about 8 cps to about 200 cps;

(b) printing the ink on a substrate surface to form
15 an image; and

(c) subjecting the image to actinic radiation or thermal energy to form a cured image.

30. The method of claim 29 wherein the actinic radiation is a beam of electrons.

20 31. The method of claim 29 wherein the energy curable ink contains a polymerization initiating system activatable by actinic radiation, and wherein the actinic radiation is ultraviolet radiation.


32. The method of claim 29 wherein the image is
25 subjected to ultraviolet radiation, a beam of electrons, or thermal energy.

33. The method of claim 27 wherein the thermal energy is radiant or conductive thermal energy.

34. A method of ink jet printing and curing an ink
30 jet ink comprising the steps of:

(a) preparing an energy curable ink jet ink having a pigment and a rheological additive of the structure:

35



wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P, and s is an integer from 1 to

5 3; and an energy curable liquid vehicle; wherein the ink is substantially free of fugitive solvent and has a viscosity ranging from about 3 cps to about 20 cps;

(b) printing the ink on a substrate surface to form an image; and

10 (c) subjecting the image to actinic radiation or thermal energy to form a cured image.

35. The method of claim 34 wherein the actinic radiation is a beam of electrons.


36. The method of claim 34 wherein the energy
15 curable ink contains a polymerization initiating system activatable by actinic radiation, and wherein the actinic radiation is ultraviolet radiation.

37. The method of claim 34 wherein the image is subjected to ultraviolet radiation, a beam of electrons
20 or thermal energy.

38. The method of claim 37 wherein the thermal energy is radiant or conductive thermal energy.

39. An energy curable ink jet ink comprising: a pigment; a rheological additive having the structure:

25




wherein P is the residue of an organic colorant, Y is a polyalkylene oxide moiety, U is a linking moiety
30 covalently bonding Y to P, and s is an integer from 1 to 3 and; an energy curable liquid vehicle; wherein the ink is substantially free of fugitive solvent and has a viscosity ranging from about 3 cps to about 20 cps.

40. The ink of claim 39 wherein the polyalkylene oxide moiety is an ethylene oxide polymer.
35

41. The ink of claim 39 wherein the polyalkylene oxide moiety is an ethylene oxide/propylene oxide copolymer.

42. The ink of claim 41 wherein the copolymer has the general formula:

- 5 42. The ink of claim 41 wherein the copolymer has the general formula:



10

wherein n is about 4 to about 400; Q is H, CH₃ or a combination thereof; and Q' is a C₁-C₆ alkyl moiety.

15

43. The ink of claim 42 wherein n is about 4 to 35 about 60.


44. The ink of claim 39 wherein P is a residue of an azo pigment, phthalocyanine pigment, dioxazine pigment, quinacridone pigment, perylene pigment, or perinone pigment.

45. The ink of claim 39 wherein U is a covalent bond, or a multivalent moiety selected from the group consisting of C₁-C₆ alkyl, -NHSO₂-, -O-, -CO-, -COO-, -N=, and -CONH-.

46. The ink of claim 39 where s has the value 1 or 2.

47. The ink of claim 39 wherein the rheological additive is an azomethine having the general formula:

35




5

wherein Y is the alkylene oxide polymer containing about
 10 to about 200 groups; R and R¹ are independently selected
 from the group consisting of H, CH₃, OCH₃, OCH₂CH₃, and Cl;
 n is an integer from 1 to 5; X is selected from the group
 consisting of C₁, CH₃, and OCH₃; and Z is selected from
 the group consisting of O and N-Y.

15

48. The ink of claim 39 wherein the additive is an
 azomethine having the general formula:

20




25

wherein Y is the polyalkylene oxide polymer containing
 about 4 to about 20 repeat units; R¹ is H, CH₃, OCH₃,
 30 OCH₂CH₃, or Cl; n is an integer from 1 to 5; R₂ is CH₃ or
 COOCH₂CH₃; R³ is H or CH₃; and X1 is Cl or OCH₃.

49. The ink of claim 39 wherein the additive is a
 diarylide having the general formula:

35




5

10 wherein: R^1 and R^5 are independently selected from the group consisting of C_1 - C_4 - alkyl, C_1 - C_4 alkoxy, and halogen; m and p are independently integers of 0 to 5; X^2 is selected from the group consisting of C_1 , CH_3 , and OCH_3 ; U^2 comprises a divalent bridging moiety selected
 15 from the group consisting of C_1 - C_6 alkyl, $-NHSO_2-$, $-O-$, $-CO-$, $-COO-$, and $-CONH-$; Y^1 comprises the polyalkylene oxide moiety having a number average molecular weight of about 200 to 10,000; and k and l are independently
 20 integers of 0 or 1, with the proviso that for at least 50 wt.% of the pigment composition, k and l are both equal to 0, and for at least 3 wt.% of the pigment composition 5 k and/or l are equal to 1.


50. The ink of claim 39 wherein the additive is an azomethine having the general formula:

25




30

wherein Y is the polyalkylene oxide polymer containing about 4 to about 20 repeat units; R^6 is independently
 35 selected from the group consisting of Cl , OCH_3 , CH_3 , OC_2H_5 , C_2H_5 , and $CONH_2$; R^7 is independently selected from the group consisting of Cl , OCH_3 , CH_3 , NO_2 , OC_2H_5 , C_2H_5 , $CONH_2$, SO_3H , OH and $COOH$; and a and b are independently integers of 0 to 5.



wherein Y has the general formula:



20 to wherein n is about 4 to about 400, and a, b, c and d are integers independently from about 0 to about 4, provided at least one of them is 1; Q is H, CH₃ or a combination thereof; and Q' is a C₁-C₆ alkyl moiety.

25 52. The ink of claim 39 wherein the pigment is selected from the group consisting of Pigment Yellow 1, Pigment Yellow 3, Pigment Yellow 12, Pigment Yellow 13, Pigment Yellow 14, Pigment Yellow 17, Pigment Yellow 37, Pigment Yellow 63, Pigment Yellow 65, Pigment Yellow 73, 30 Pigment Yellow 74, Pigment Yellow 75, Pigment Yellow 83, Pigment Yellow 97, Pigment Yellow 98, Pigment Yellow 106, Pigment Yellow 114, Pigment Yellow 121, Pigment Yellow 126, Pigment Yellow 127, Pigment Yellow 136, Pigment Yellow 174, Pigment Yellow 176, Pigment Yellow 188, 35 Pigment Orange 5, Pigment Orange 13, Pigment Orange 16, Pigment Orange 34, Pigment Red 2, Pigment Red 9, Pigment Red 14, Pigment Red 17, Pigment Red 22, Pigment Red 23, Pigment Red 37, Pigment Red 38, Pigment Red 41, Pigment Red 42, Pigment Red 112, Pigment Red 146, Pigment Red

5 170, Pigment Red 196, Pigment Red 210, Pigment Red 238,
Pigment Blue 15, Pigment Blue 15:1, Pigment Blue 15:2,
Pigment Blue 15:3, Pigment Blue 15:4, Pigment Green 7,
Pigment Green 36, Pigment Violet 23, and Pigment Black
7.

10 53. The ink of claim 39 wherein the pigment is
distinct from P.

54. The ink of claim 39 wherein the pigment is the
same as P.

15 55. The ink of claim 54 wherein the ink contains an
additional distinct pigment.

56. The ink of claim 39 wherein the energy curable
liquid vehicle is a ring opening polymerizable
composition.

20 57. The ink of claim 56 wherein the polymerizable
composition is a cationic polymerizable system comprising
one or more mono-functional and/or multi-functional
expected monomers.

25 58. The ink of claim 39 further comprising a
polymerization initiating system activatable by actinic
radiation.

59. The ink of claim 39 wherein the energy curable
liquid vehicle is a free radical addition polymerizable
system comprising an ethyleneically unsaturated
monofunctional or multi-functional monomer.

30 60. The ink of claim 59 wherein the ink contains a
free radical generating, addition polymerization
initiating system activatable by actinic radiation.

61. The ink of claim 39 wherein the ink contains a
surface active agent, a wax, or a combination thereof.

35

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/27038

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C09B69/00 C09D11/10 C09B67/22 C09D11/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C09B C09D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 137 630 A (SUN CHEMICAL CORP) 17 April 1985 (1985-04-17) page 1, line 16 -page 4, line 1 page 8, line 11 - line 21 & US 4 468 255 A cited in the application	1-5, 7-12, 14-16, 47,49,50
A	WO 92 13911 A (SUN CHEMICAL CORP) 20 August 1992 (1992-08-20) page 7, line 1 - line 8; claim 1 -/-	1-5, 7-12, 14-16, 47,49,50

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

3 May 2000

Date of mailing of the international search report

15/05/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Ketterer, M

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 99/27038

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 946 508 A (SCHWARTZ RUSSELL J ET AL) 7 August 1990 (1990-08-07) cited in the application column 1, line 57 -column 2, line 48	1-5, 7-12, 14-16, 47-50
A	WO 91 14744 A (SUN CHEMICAL CORP) 3 October 1991 (1991-10-03) page 2, line 1 -page 3, paragraph 3 & US 5 024 698 A cited in the application	1-5, 7-12, 14-16, 47, 49, 50
A	EP 0 399 458 A (SUN CHEMICAL CORP) 28 November 1990 (1990-11-28) the whole document & US 4 946 508 A cited in the application & US 4 946 509 A cited in the application	1-5, 7-12, 14-16, 47-50
A	WO 92 13922 A (SUN CHEMICAL CORP) 20 August 1992 (1992-08-20) page 2, line 35 -page 4, line 10 & US 5 062 894 A cited in the application	1-5, 7-12, 14-16, 47, 49, 50

INTERNATIONAL SEARCH REPORT

Information on patent family members

Informatic Application No

PCT/US 99/27038

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0137630 A	17-04-1985	US 4468255 A AT 41170 T AU 571247 B AU 3097384 A DE 3477015 D DK 355284 A,B, JP 60063259 A	28-08-1984 15-03-1989 14-04-1988 14-02-1985 13-04-1989 11-02-1985 11-04-1985
WO 9213911 A	20-08-1992	US 5145997 A AT 153041 T CA 2103717 A DE 69219760 D DE 69219760 T DK 572463 T EP 0572463 A ES 2102494 T	08-09-1992 15-05-1997 13-08-1992 19-06-1997 23-10-1997 13-10-1997 08-12-1993 01-08-1997
US 4946508 A	07-08-1990	AT 103623 T CA 2016539 A DE 69007671 D DE 69007671 T DK 399458 T EP 0399458 A ES 2063193 T JP 3009957 A MX 171109 B PT 94126 A,B	15-04-1994 23-11-1990 05-05-1994 14-07-1994 24-05-1994 28-11-1990 01-01-1995 17-01-1991 30-09-1993 08-02-1991
WO 9114744 A	03-10-1991	US 5024698 A AT 157690 T CA 2078862 A DE 69127540 D DE 69127540 T DK 524941 T EP 0524941 A ES 2107455 T FI 923865 A	18-06-1991 15-09-1997 23-09-1991 09-10-1997 22-01-1998 14-04-1998 03-02-1993 01-12-1997 28-08-1992
EP 0399458 A	28-11-1990	US 4946508 A US 4946509 A AT 103623 T CA 2016539 A DE 69007671 D DE 69007671 T DK 399458 T ES 2063193 T JP 3009957 A MX 171109 B PT 94126 A,B	07-08-1990 07-08-1990 15-04-1994 23-11-1990 05-05-1994 14-07-1994 24-05-1994 01-01-1995 17-01-1991 30-09-1993 08-02-1991
WO 9213922 A	20-08-1992	US 5062894 A AT 150475 T CA 2103718 A DE 69218427 D DE 69218427 T DK 586391 T EP 0586391 A ES 2101091 T	05-11-1991 15-04-1997 13-08-1992 24-04-1997 23-10-1997 08-09-1997 16-03-1994 01-07-1997

Form PCT/ISA/210 (patent family annex) (July 1992)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 : C09B 69/00, C09D 11/10, C09B 67/22, C09D 11/02	A1	(11) International Publication Number: WO 00/31189	(43) International Publication Date: 2 June 2000 (02.06.00)
---	----	--	--

(21) International Application Number: PCT/US99/27038

(22) International Filing Date: 15 November 1999 (15.11.99)

(30) Priority Data:
09/198,113 23 November 1998 (23.11.98) US(71) Applicant: SUN CHEMICAL CORPORATION [US/US]; 222
Bridge Plaza South, Fort Lee, NJ 07024 (US).(72) Inventors: LAKSIN, Mikhail; 2278 Redwood Road, Scotch
Plains, NJ 07076 (US). CHATTERJEE, Subhankar; 60
Norma Road, Hampton, NJ 08827 (US). SCHWARTZ,
Russell; 8300 Monte Drive, Cincinnati, OH 45232 (US).
MERCHAK, Paul, A.; 10063 Fox Chase Drive, Loveland,
OH 45140 (US). AURENTY, Patrice; 27 Charter Oak,
Woodridge, NJ 07075 (US). STONE, Edward; 4 Inwood
Road, Morris Plains, NJ 07950 (US). KOTORA, Gordon;
29 Belgrade Avenue, Clifton, NJ 07013 (US).(74) Agent: PERSLEY, Sidney; 222 Bridge Plaza South, Fort Lee,
NJ 07024 (US).(81) Designated States: CA, JP, KP, European patent (AT, BE, CH,
CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT,
SE).**Published***With international search report.
Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.*

(54) Title: ENERGY CURABLE GRAVURE AND INK JET INKS INCORPORATING GRAFTED PIGMENTS

(57) Abstract

Solvent-free, energy curable low viscosity gravure and ink jet inks which contain a pigment; a rheological additive having the structure $P-(U-Y)_s$, wherein P is the residue of an organic pigment or dye, Y is a polyalkylene oxide moiety, U is a linking moiety covalently bonding Y to P and s is an integer from 1 to 3; and an energy curable liquid vehicle which may be an ultraviolet cationic, thermal cationic or a free radical initiated polymerization system, cured by actinic radiation; and optionally containing a photoinitiating system.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon	KR	Republic of Korea	PL	Poland		
CN	China	KZ	Kazakhstan	PT	Portugal		
CU	Cuba	LC	Saint Lucia	RO	Romania		
CZ	Czech Republic	LI	Liechtenstein	RU	Russian Federation		
DE	Germany	LK	Sri Lanka	SD	Sudan		
DK	Denmark	LR	Liberia	SE	Sweden		
EE	Estonia			SG	Singapore		